

Purolite® C100E

Gel Strong Acid Cation Resin - Sodium Form

PRODUCT DATA SHEET

Principal Applications

- Domestic water softening
- Food and beverage processing
- Industrial softening

Advantages

- Efficient regeneration
- Good kinetic performance
- Low extractables

Typical Physical and Chemical Characteristics

Polymer Structure	Gel polystyrene crosslinked with DVB
Appearance	Amber, clear spherical beads
Functional Group	Sulfonic acid
Ionic Form as Shipped	Na ⁺
Total Capacity (min.)	1.9 eq/l (41.5 Kgr/ft ³) (Na ⁺ form)
Moisture Retention	46 - 50 % (Na ⁺ form)
Particle Size Range	300 - 1200 µm
<300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling Ca ²⁺ → Na ⁺	8 %
Reversible Swelling, Na ⁺ → H ⁺ (max.)	10 %
Specific Gravity	1.27
Shipping Weight (approx.)	800 - 840 g/l (50 - 52.5 lb/ft ³)
Temperature Limit	120°C (250°F)



Americas

T +1 610.668.9090
F +1 484.384.2751
americas@purolite.com

Europe

T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific

T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com